

WE HELP YOU BUILD

Product Data Sheet

BETOCRETE®-C35

CRYSTALLINE WATERPROOFING CONCRETE ADMIXTURE

Product Description:

BETOCRETE®-C35 is a crystalline technology concrete admixture used to produce permanently active waterproof concrete in:

- Water retaining structures; potable water tanks, sewage treatment plants, and septic tanks.
- Water excluding structures; retaining walls, tunnels, elevator pits, and dams.
- Below grade structures; piles foundations, basements.
- Mass concrete.

Advantages:

- Permanently active; will self-heal future static cracks up to 400 microns.
- Improved final strength.
- Provides additional protection to reinforcement steel by reducing chloride ion diffusion.
- Can be used in a high w/c ratio (up to 0.55) concretes.
- Withstands high water pressures (up to 14 bars).
- Compatible with most types of concrete admixtures.
- Eliminates the need for surface waterproofing.

Technical Properties:

Colour : grey.

Form : powder.

Bulk density : 1.04 g/cm³.

Processing temp : +8°C to +30°C

Application temp : from +5°C

Dosage Range:

The dosage amount depends on the concrete/mortar mix design and the reactivity of the cement. Trial applications must be conducted to find the suitable amount. The recommended dosage rate is 0.8 – 1.5% by weight of CEM.

Instructions for Use:

Dosage in mortars:

Add BETOCRETE®-C35 to the aggregate and approx. 40% of the mix water. Mix at least 2 minutes before adding the remaining water and cement.

Dosage in ready-mix factory:

Add BETOCRETE®-C35 to the aggregate and mix at least 30 s before adding water and cement. Continue mixing for at least 45 s until the concrete mix has reached its working properties.

Dosage in a batch truck:

The addition of BETOCRETE®-C35 on the job site (batch truck) does not happen in powder form but as a suspension in water. Mix the required amount of BETOCRETE®-C35 with water in a suitable vessel and add this slurry completely into the mixing drum. The mixing ratio is approx. 1:1, add approx. 5 I water to a 5 kg bag BETOCRETE®-C35. The required mixing time can be estimated as 1 minute per m³ drum contents, but min. 5 minutes. Make sure that the additional slurry water does not increase the water/cement ratio above the projected value. Otherwise, the water amount must be reduced from the mixing water dosage at the batch plant. The working time after addition of



WE HELP YOU BUILD

Product Data Sheet

BETOCRETE®-C35 depends on the reactivity of the used cement and can either be prolonged or shortened. The addition of a concrete retarder like RUXLITH-T5 (VZ) or REMITARD-20 (BV) may be required when using Portland Cement Type I, II or III. Suitability tests accord. to valid standards and norms have to be carried out prior to application.

Estimating & Supply:

25 kg bags.

Cleaning & Equipment Maintenance:

Regular water flushing of dispensing equipment will prolong service life and reduce breakdowns. Use REINIT-BM on internal metal surfaces subject to contact with concrete in concrete mixers, batch plants and truck mixers regularly to prevent concrete crust formations. Use REINIT-R to remove hardened concrete crusts.

Storage & Shelf-life:

BETOCRETE®-C35 has a shelf-life of 12 months when stored dry at +20° C in original, unopened bags

Special Advice:

- Concrete modified with BETOCRETE®-C35 may tend to effloresce depending on the composition.
- Aggregates must have a continuous sieve line.
- It is recommended to perform compatibility tests with other admixtures as required.
- Concrete, modified with BETOCRETE®-C35 must be produced, placed and finished in accordance with valid norms.
- BETOCRETE®-C35 is non-corrosive and has no adverse effects on the reinforcement.
- Protect surrounding areas against the influence of BETOCRETE®-C35.

- It is rarely possible that BETOCRETE-C35 influences the setting of the concrete. Our products RUXOLITH-T5 (VZ) and REMITARD-20 (BV) have proven to be effective retarders.
- Never apply BETOCRETE®-C35 powder into mixed (wet) concrete or mortar mixes as this will increase the risk of lump formation. A homogeneous dispersion of BETOCRETE®-C35 cannot be expected under these conditions.

Health & Safety:

Please adhere to the valid European Materials Safety Data Sheet (MSDS)!

